

Architectural Coatings

*Speed Cryl* Exterior 100% Acrylic Latex Semi-Gloss

## GENERAL DESCRIPTION

*Speed Cryl* is a professional quality exterior 100% acrylic latex that provides an economical option for good adhesion, hiding and coverage on a variety of exterior substrates. It is specifically formulated to meet the professional application needs of high volume new home, multi-family, commercial and large repaint projects. It offers a full body feel and provides a good balance of build capabilities and sag resistance for spray, brush, or roll application.

## RECOMMENDED SUBSTRATES

|                 |                    |      |
|-----------------|--------------------|------|
| Aluminum Siding | Fiber Cement Board | Wood |
| Brick           | Masonry            |      |
| Concrete        | Metal              |      |

## CONFORMANCE STANDARDS

Compliant with all US VOC regulations as of 08/2026

## TINTING AND BASE INFORMATION

|          |                     |
|----------|---------------------|
| 56-510XI | White & Pastel Base |
| 56-520XI | Midtone Base*       |
| 56-540XI | Ultra Deep Base*    |

\*Must be tinted before use. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

## PACKAGING

1-Gallon (3.78 L)  
5-Gallon (18.9 L)

## PRODUCT DATA

|                        |                                       |
|------------------------|---------------------------------------|
| <b>PRODUCT TYPE:</b>   | 100% Acrylic Latex                    |
| <b>SHEEN:</b>          | Semi-Gloss: 35-65 @60°                |
| <b>VOLUME SOLIDS*:</b> | 34% +/- 2%                            |
| <b>WEIGHT SOLIDS*:</b> | 42% +/- 2%                            |
| <b>WEIGHT/GALLON*:</b> | 9.6 lbs. (4.4 kg) +/- 0.2 lbs. (91 g) |
| <b>VOC:</b>            | < 50 g/L (0.4 lbs./gal.)              |

\*Product data calculated on product 56-510XI.

**COVERAGE:** Up to 400 sq. ft. (37 sq. meters) per U.S. gallon (3.78 L) on primed, smooth, nonporous surfaces.

|                     |          |
|---------------------|----------|
| Wet Film Thickness: | 4 mils   |
| Wet Microns:        | 102      |
| Dry Film Thickness: | 1.4 mils |
| Dry Microns:        | 36       |

Coverage figures do not include material loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some colors, drastic color changes, or porous surfaces may require more than one coat to achieve a uniform finish.

**DRYING TIME:** Dry time @ 77°F (25°C); 50% relative humidity.  
To Touch: 30-60 minutes  
To Recoat: 2-4 hours  
To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, color, film build, and air movement. For example, product applied at 35°F (2°C) would require a minimum of 24 hours before recoat.

**CLEANUP:** Clean tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)

## FEATURES / BENEFITS

### Features

- 100% Acrylic Latex
- Application Down to 35°F (2°C)
- Full-Bodied Application
- Good Adhesion
- Good Hiding Power
- Resists Mildew on the Dry Paint Film
- < 50 g/L VOC

### Benefits

- Offers good weather resistance
- Extends the painting season
- Provides a good balance of build capabilities and sag resistance
- Offers good durability
- Provides a uniform finish
- Stays clean longer
- Meets national VOC regulations

## GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Stucco, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. An appropriate primer is recommended for all uncoated surfaces and special substrates, such as tannin staining wood, new or chalky masonry, and bare metal.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted, NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**ALUMINUM SIDING:** Siding may present potential adhesion problems. Prime prior to topcoating. A specialty primer may be required if the original painted surface has degraded to the substrate. Topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion.

**BRICK:** New brick and mortar should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended. Painting glazed brick is not recommended due to potential adhesion problems.

**CONCRETE and MASONRY:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

**FERROUS METAL:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

**FIBER CEMENT:** Fiber cement board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to topcoating.

**WOOD:** Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface, then prime.

## RECOMMENDED PRIMERS

|                    |                                          |
|--------------------|------------------------------------------|
| Aluminum Siding    | 17-921XI                                 |
| Brick              | 4-503, 4-603XI, 17-921XI,<br>17-6001     |
| Concrete           | 4-503, 4-603XI, 17-921XI,<br>17-6001     |
| Ferrous Metal      | 90-1912, 90-1907, 90-1908,<br>4160, 4360 |
| Masonry            | 4-503, 4-603XI, 17-921XI,<br>17-6001     |
| Fiber Cement Board | 4-503, 4-603XI, 17-921XI,<br>17-6001     |
| Wood               | 17-921XI, 17-6001                        |

## LIMITATIONS OF USE

**FOR EXTERIOR USE ONLY.** Apply only when air, surface, and product temperatures are between 35°F (2°C) and 90°F (32°C) and at least 5°F (3°C) above the dew point. Air and surface temperatures must remain between 35°F (2°C) and 90°F (32°C) for the next 48 hours. Avoid painting in direct sunlight or on hot surfaces. Do not apply late in the day when dew and condensation are likely to form or if rain or snow is expected. On large expanses of metal, temperatures must be 50°F (10°C) or higher.

Not recommended for use on steps, floors, or vinyl surfaces.

### PROTECT FROM FREEZING.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae. Examples of these conditions include, but are not limited to, under eaves, behind shrubbery and trees, and in areas that are consistently damp with little to no direct sunlight.

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one container of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high-quality brush, roller (nap size – 3/8" for smooth surfaces and up to 3/4" for rough or textured surfaces), paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly for 2-4 hours before applying the next coat.

**Airless Spray:** For airless spray application, use tip size .015" to .021" and pressure range of 1500 to 2000 psi. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Nylon/Polyester Brush

**Roller:** 3/8" - 3/4" nap roller cover

**Thinning:** Do not thin.

**Permissible temperatures during application:**

Material: 35 to 90°F (2 to 32°C)

Ambient: 35 to 100°F (2 to 38°C)

Substrate: 35 to 100°F (2 to 38°C)

## PRECAUTIONS

For warning information, please refer to the product label and SDS available at the online listing for this product at [www.pittsburghpaintsco.com](http://www.pittsburghpaintsco.com). Keep container tightly closed and sealed until ready for use. SDS, spill, and emergency information are available by calling 1-833-477-1553.

© 2026 The Pittsburgh Paints Co. All Rights Reserved. The *P Logo* & *Pittsburgh Paints* are trademarks of The Pittsburgh Paints Co. *Speed Cryl* is a registered trademark of PPG Industries Ohio, Inc. used under license by The Pittsburgh Paints Co.

The Pittsburgh Paints Co. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.



**PITTSBURGH  
PAINTS CO.**

The Pittsburgh Paints Company  
500 Cranberry Woods Drive  
Cranberry Township, PA 16066  
[www.pittsburghpaints.com](http://www.pittsburghpaints.com)

Technical Services  
1-800-441-9695

56-510XI - 8/2026