

GENERAL DESCRIPTION

SUN-PROOF Exterior House and Trim 100% Acrylic Latex Paint is specifically formulated to meet the performance requirements of the residential and commercial markets.

The new and improved formula provides excellent durability, great dirt resistance, low temperature application and excellent adhesion.

SUN-PROOF can be used on properly prepared and primed new and previously painted exterior siding, doors, trim and windows.

On vinyl siding, do not use shades that are darker than the original as it could lead to warping.

RECOMMENDED SUBSTRATES

Aluminum Siding	Brick
Concrete	Fibre Cement Siding
Masonry	Primed Metal
Stucco	Vinyl Siding*
Wood	

*See "Limitations of use"

CONFORMANCE STANDARDS

- Complies with the Canadian Volatile Organic Compound Concentration Limits for Architectural Coatings Regulations
- Meets MPI #11Latex, Exterior Semi-Gloss (MPI Gloss Level 5)
- Meets MPI Green Performance Standard (GPS-1)

TINTING AND BASE INFORMATION

Refer to the appropriate colour formula book, automatic tinting equipment, and/or computer colour-matching system for colour formulas and tinting instructions.

78-45XIC	Super White
78-811XIC	White/Pastel Base
78-815XIC	Midtone Base*
78-300XIC	Ultra Deep Base*

*Must be tinted before use.

Some colours, drastic colour changes, or porous substrates may require more than one coat to achieve a uniform finish.

PACKAGING

946 mL

3.78 L

Not all products are available in all sizes.

PRODUCT DATA

PRODUCT TYPE: 100% Acrylic Latex Paint
SHEEN: Semi-Gloss: 40 to 50 %
 (60° Gloss Meter)

VOLUME SOLIDS*: 38% ± 2%

WEIGHT SOLIDS*: 51% ± 2%

VOC*: < 50 g/L

DENSITY*: 1.3 kg/L

*Product data calculated on product 78-811XIC.

SPREADING RATE PER COAT Approximately 37.2 m² (400 ft²) per 3.78 litres on primed, smooth, nonporous surfaces.

Wet Film Thickness: 4.0 mils (102 microns)

Dry Film Thickness: 1.5 mils (39 microns)

Coverage figures do not include loss due to surface irregularities and porosity or material losses due to application method or mixing.

DRYING TIME: Dry time @ 25°C (77°F); 50% relative humidity.

To Touch: 1 hour

To Recoat: 4 hours minimum

To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, film build, colour, and air movement. For example, product applied at 2°C would require a minimum of 24 hours before recoat.

Permissible temperatures during the application:

Material:	2 to 32°C	35 to 90°F
Ambient:	2 to 38°C	35 to 100°F
Substrate:	2 to 38°C	35 to 100°F

CLEANUP: Remove as much product quantity as possible and clean tools with lukewarm soapy water immediately after use.

DISPOSAL: Consult your municipality in order to dispose of paint residues according to environmental regulations.

Do not pour down a drain or storm sewer.

FLASH POINT: Over 93°C (200°F)

FEATURES / BENEFITS

Features

Excellent adhesion
 Great dirt resistance
 100% acrylic latex formulation
 Low VOC formula <50 g/L

 Thick, full-bodied formula
 Mildew resistance on the paint film
 Durable, tough finish
 Application down to 2°C (35°F)

Benefits

Minimizes cracking and peeling.
 Stays cleaner longer.
 Excellent longevity and overall durability.
 Complies with the Canadian Volatile Organic Compound Concentration Limits for Architectural Coatings Regulations.
 Smoother application, minimizes drips and runs.
 Stays cleaner longer.
 Resists chipping providing long-lasting beauty
 Extends the painting season.

LIMITATIONS OF USE

FOR EXTERIOR USE ONLY.

Not recommended for use on steps or floors.

The following surfaces require an appropriate speciality primer:

- Woods such as redwood, cedar, mahogany and Douglas fir containing tannic acid which tends to migrate to the surface.
- High alkaline surfaces such as concrete and masonry.
- Bare metal.

Colour selection for use over vinyl siding is limited. Do not use shades that are darker than the original as it could lead to warping.

While this product provides a mildew-resistant coating, growth may still occur if the substrate is not properly prepared prior to painting or if the substrate is consistently exposed to conditions conducive to mould, mildew, and algae.

PROTECT FROM FREEZING.

Apply when air and surface temperatures are above 2°C, and when surface temperature is at least 3°C above the dew point.

For optimum application properties, bring product to at least 10°C prior to the application. Air and surface temperatures must remain above 2°C for at least 24 hours after the application. Avoid painting late in the day when dew and condensation are likely to form or if rain or snow is expected. Do not apply in direct sunlight.

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing.

Mildew: Remove mildew with a solution of household bleach (1 part household bleach to 3 parts of water). Before use, be sure to read and follow the instructions and warnings on the label.

Chalking: Remove chalk residue with a wire brush. Rinse thoroughly with hose or power wash and let surface dry.

Sand all glossy, rough or patched surfaces. Feather back all rough edges to sound surface by sanding.

PRECAUTION: Dry sanding will give rise to dust and/or hazardous fumes. Wet sanding should be used wherever possible. Wear suitable respiratory protective equipment when exposure cannot be avoided by adequate local ventilation. Clean up carefully with a HEPA vacuum and a wet mop. Follow these instructions to control exposure to hazardous substances that may be released during surface preparation. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Contact a regional Health Canada office for more information.

Prime all bare wood, metal, chalky or porous surfaces with an appropriate high quality primer.

Aluminum: This substrate may present potential adhesion problems. Any coating applied directly to aluminum should be spot applied, allowed to cure overnight, and then evaluated for adhesion. If adhesion is good, the application may proceed.

Concrete, fibre cement siding, stucco and masonry:

- Prior to priming or top coating, substrate should cure for at least 30 days and preferably 90 days, the moisture content must be less than 12% and the pH must be less than 10. If pH is greater than 10, prime with an alkali resistant primer.
- **Efflorescence:** Remove efflorescence by pressure washing or cleaning with diluted muriatic acid. Before use, be sure to read and follow the instructions and warnings on the label.
- **Brick:** Painting glazed brick is not recommended due to potential adhesion problems.
- **Fibre cement siding:** Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to top coating. Surface chalk from the curing or aging process should be removed then sealed with an appropriate sealer to rebind and restore the surface to a sound condition.

Ferrous metal: Prior to priming and top coating, the surface must be cleaned thoroughly to remove any dust, rust, oil and surface contaminants.

Vinyl siding: Vinyl and similar architectural plastics may present potential adhesion problems. A primer may be required to promote proper adhesion. Consult the manufacturer's guidelines prior to painting. Primer and topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. Check adhesion by applying a piece of masking tape. If adhesion is good, the application may proceed. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion. Do not use shades that are darker than the original as it could lead to warping.

Wood: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, and then primed. Any knots or resinous areas must be primed before painting. Countersink all nails or screws, putty flush with the surface, then prime prior to painting.

Moisture content:

Prior to the application of coatings, the moisture content of the substrate should be checked by one of the following methods:

- Electrode-type moisture meter. For this method, coating can be applied if readings of less 5% moisture content (electrical impedance) or 12% (electrical conductivity).
- Placing a sheet of plastic on the concrete surface for the same length of time the repair material would take to cure (normally 24 hours @ 25°C). If, after this time, there is visible moisture, a poor bond may result. Putty all holes and caulk all cracks and open seams to prevent water penetration prior to priming and painting.

Before use, be sure to read and follow the instructions and warnings on the label.

Contact your local representative for any additional surface preparation guidelines.

RECOMMENDED PRIMERS

Aluminum Siding:	self-priming, 17-921XIC	Aluminum:	90-712C
Brick:	17-921XIC	Concrete:	17-921XIC
Ferrous Metal:	6-208, 6-212	Fibre Cement Siding:	4-809C
Masonry:	17-921XIC	Stucco:	4-809C
Vinyl Siding:	self-priming, 17-921XIC	Wood:	17-921XIC

This product is self-priming on different surfaces in good condition and properly prepared.

The following surfaces may require an appropriate speciality primer:

- Woods such as redwood, cedar, mahogany and Douglas fir containing tannic acid which tends to migrate to the surface.
- High alkaline surfaces such as concrete and masonry.
- Bare metal.

APPLICATION INFORMATION

Stir thoroughly before use and occasionally during use. When using more than one container of the same colour, intermix to ensure colour uniformity.

KEEP OUT OF REACH OF CHILDREN. USE WITH ADEQUATE VENTILATION. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available from your retailer, through our website or by calling 1-800-463-7426.

Application Equipment: Apply with a high quality synthetic brush, roller, paint pad, or by spray equipment. Where necessary, apply a second coat.

Brush: High quality polyester/nylon brush.

Roller: 10 to 20 mm (3/8 – 3/4 in.) nap synthetic roller cover.

Airless Spray: Pressure 2000 psi, tip 0.015 in. - 0.021 in.

Spray equipment must be handled with due care and in accordance with the manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Thinning: No thinning is usually required.

PRECAUTIONS

Keep out of the reach of children. Keep containers tightly closed and sealed until ready for use.

Before using the products listed in this publication, carefully read each product label and follow directions for its use. Use personal protective equipment as required. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation.

Note: These warnings encompass the product series.

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION. Avoid breathing vapours, spray or mists. Avoid contact with skin and eyes. Wear protective gloves/clothing and eye/face protection.

FIRST AID: If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. In case of contact, immediately flush skin with plenty of water while removing contaminated clothing and shoes. Get medical attention if irritation develops. If inhaled, remove to fresh air. If experiencing respiratory symptoms call poison centre or doctor/physician.

For workplace use, an SDS are available from your retailer, through our website or by calling 1 800 463-7426.

EMERGENCY SPILL INFORMATION: 1 514 645-1320 or 1 800 463-7426.

LIMITED WARRANTY

PPG Architectural Coatings Canada, Inc. warrants performance of its products to its intended use if properly applied in accordance with the label directions and the specifications of the technical data sheet. Having no control over the application methods and conditions or the circumstances related to its use, no other warranty, expressed or implied, statutory or otherwise is given. This limited warranty extends only to the original purchaser of the product and is not transferable or assignable. If the product fails to conform to this limited warranty, we will, at your option, furnish replacement product or refund the purchase price. This limited warranty excludes (1) labour or costs of labour for the application or removal of any product and (2) all other direct, indirect, incidental, special or consequential damages.

The PPG Paints Logo & Design is a trademark of PPG Industries Ohio, Inc. SUN-PROOF is registered trademark of PPG Architectural Finishes, Inc. MPI and MPI Green Performance are trademarks of Master Painters Institute, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1 866 660-2220.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpaints.com

PPG Architectural Coatings Canada Inc.
2505, rue de la Metropole
Longueuil (Quebec) Canada J4G 1E5

Technical Services 450 442-2220
1 866 660-2220
Fax: 450 679-8893
1 800 278-8893

Architect/Specifier
1-888-PPG-IDEA