

Architectural Coatings

*Performance Flat Interior Wall & Ceiling Paint*

## GENERAL DESCRIPTION

*Performance Flat* Interior Paint is designed as a latex paint with excellent touch up properties. It is an economical solution for high volume projects requiring a high hiding product with excellent touch up when applied by spray, brush and/or roll. It dries to a uniform flat finish to help hide tape joints and surface imperfections. *Performance Flat* Interior Paint is self-priming on drywall and meets the needs of painters, building contractors and building managers.

## RECOMMENDED SUBSTRATES

|                      |                          |
|----------------------|--------------------------|
| Concrete/Masonry     | Gypsum Wallboard-Drywall |
| Concrete Block (CMU) | Plaster                  |
| Ferrous Metal        | Wood                     |

## CONFORMANCE STANDARDS

Compliant with all US VOC Regulations as of 10/2026

## TINTING AND BASE INFORMATION

|         |                  |
|---------|------------------|
| 61-1155 | Antique White    |
| 61-1157 | Lulled Beige     |
| 61-1171 | Toasted Almond   |
| 61-1172 | Southern Breeze  |
| 61-1174 | Moth Gray        |
| 61-1175 | Whiskers         |
| 61-1176 | Synchronicity    |
| 61-1177 | Ashen            |
| 61-1178 | Elusion          |
| 61-1179 | Commercial White |

## PRODUCT DATA

|                        |                                        |
|------------------------|----------------------------------------|
| <b>PRODUCT TYPE:</b>   | Vinyl Acrylic Latex                    |
| <b>SHEEN:</b>          | Flat: 0-2 @85°                         |
| <b>VOLUME SOLIDS*:</b> | 25% +/- 2%                             |
| <b>WEIGHT SOLIDS*:</b> | 42% +/- 2%                             |
| <b>WEIGHT/GALLON*:</b> | 10.8 lbs. (4.9 kg) +/- 0.2 lbs. (91 g) |
| <b>VOC:</b>            | < 50 g/L (0.4 lbs./gal.)               |

\*Product data calculated on product 61-1179.

**COVERAGE:** Approximately 400 sq. ft. (37 sq. meters) per U.S. gallon (3.78 L) on primed, smooth, nonporous surfaces.

|                     |          |
|---------------------|----------|
| Wet Film Thickness: | 4.0 mils |
| Wet Microns:        | 102      |
| Dry Film Thickness: | 1.0 mils |
| Dry Microns:        | 25       |

Coverage figures do not include material loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some colors, drastic color changes, or porous surfaces may require more than one coat to achieve a uniform finish.

**DRYING TIME:** Dry time @ 77°F (25°C); 50% relative humidity.

|               |            |
|---------------|------------|
| To Touch:     | 30 minutes |
| To Recoat:    | 4 hours    |
| To Full Cure: | 30 days    |

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

**CLEANUP:** Clean tools with warm, soapy water.

**DISPOSAL:** Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

**FLASH POINT:** Over 200°F (93°C)

## FEATURES / BENEFITS

### Features

Excellent Touch-Up  
Great Hide  
Easy Application for Spray & Backroll  
as well as Brush & Roller Applications  
Flat Finish to Help Hide Tape Joint and Surface Imperfections  
Self-Priming on Drywall  
Low VOC, < 50 g/L

### Benefits

Reduces labor expense  
Provides good surface coverage  
Can be used by any type of applicator  
  
Provides uniform finished appearance  
Can reduce the need for multiple coats  
Meets the most stringent VOC regulations nationwide

## GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Stucco, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. An appropriate primer is recommended for all uncoated surfaces and special substrates, such as tannin staining wood, new or chalky masonry, and bare metal.

**WARNING!** If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted, NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead). Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

**CONCRETE/MASONRY:** New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

**CONCRETE BLOCK (CMU):** Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler.

**FERROUS METAL:** The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

**GYPSUM WALLBOARD-DRYWALL:** Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

**PLASTER:** Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

**WOOD:** Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be sealed before painting.

## RECOMMENDED PRIMERS

|                          |                                                     |
|--------------------------|-----------------------------------------------------|
| Concrete/Masonry         | 4-603XI, 17-921XI, 3210-120XI                       |
| Concrete Block (CMU)     | 6-7, 6-15XI                                         |
| Ferrous Metal            | 90-1908, 90-1909, 90-1912                           |
| Gypsum Wallboard-Drywall | Self-Priming, 6-2, 6-4, 9-900, 12-900XI, 3210-120XI |
| Plaster                  | 4-603XI, 17-921XI, 3210-120XI                       |
| Wood                     | 6-2, 9-900, 12-900XI, 17-921XI, 3210-120XI          |

## LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors.

PROTECT FROM FREEZING.

## PACKAGING

1-Gallon (3.78 L)

5-Gallon (18.9 L)

Not all products are available in all sizes.

## APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

**Application Equipment:** Apply with a high-quality brush, roller (nap size – 3/8" for smooth surfaces and up to 3/4" for rough or textured surfaces), paint pad, or by spray equipment. Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

**Airless Spray:** For airless spray application, use tip size .015" to .021" and pressure range of 1500 to 2000 psi. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

**Brush:** Nylon/Polyester Brush

**Roller (nap roller cover):** 3/8" - 3/4"

**Thinning:** Do not thin.

**Permissible temperatures during application:**

Material: 50 to 90°F (10 to 32°C)

Ambient: 50 to 90°F (10 to 32°C)

Substrate: 50 to 90°F (10 to 32°C)

## PRECAUTIONS

For warning information, please refer to the product label and SDS available at the online listing for this product at [www.pittsburghpaintsco.com](http://www.pittsburghpaintsco.com). Keep container tightly closed and sealed until ready for use. SDS, spill, and emergency information are available by calling 1-833-477-1553.

© 2026 The Pittsburgh Paints Co. All Rights Reserved. The *P Logo & Pittsburgh Paints* are trademarks of The Pittsburgh Paints Co. *Performance Flat* is a trademark of PPG Industries Ohio, Inc. used under license by The Pittsburgh Paints Co.

The Pittsburgh Paints Co. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.



The Pittsburgh Paints Company  
500 Cranberry Woods Drive  
Cranberry Township, PA 16066  
[www.pittsburghpaints.com](http://www.pittsburghpaints.com)

Technical Services  
1-800-441-9695

61-11XX - 10/2026