



Architectural Coatings

Pure Performance Paint & Primer In One Interior Flat

GENERAL DESCRIPTION

Our premium low-odor, zero-VOC** (volatile organic compounds) flat latex base paint is designed to meet the performance requirements of the institutional, commercial and residential segments. Pure Performance Paint & Primer* in One Interior Latex is formulated to provide excellent hiding and application properties in addition to low odor, zero-VOC's**, and anti-microbial properties - a mold/mildew resisting compound has been incorporated in this paint to make the dry paint film mildew resistant. Ideal for use in occupied areas such as: hotel/motel resort properties, nursing homes, homes, schools, government facilities, retail space, office buildings, hospitals, and apartments.

*Separate primer or multiple coats may be required. See COVERAGE for details.

RECOMMENDED SUBSTRATES

Table with 2 columns: Substrate Type and Recommendation. Includes Concrete, Concrete/Masonry Block, Ferrous Metal, Gypsum Wallboard-Drywall, Plaster, and Wood.

CONFORMANCE STANDARDS

Compliant with all US VOC regulations as of 05/2024
Can help earn LEED® Credits, LEED Low Emitting Materials Credit
Can help earn LEED® Credits- LEED Material & Resources Building
Product Disclosure and Optimization- Material Ingredients Credit
Greenguard Gold Certified - Meets Strict Chemical Emission Limits and the Most Stringent Environmental Regulations
Eligible for CHPS low emitting credit (Collaborative for High Performance Schools)
CDPH (California Department of Public Health) Emissions Certified
MPI® approved in category #53, #142, #143 and #143 X-Green, (MPI Gloss Level 1)

PRODUCT INFORMATION

Table with 2 columns: Product Code and Color Name. Includes 9-100 Pure White, 9-110XI White & Pastel Base, 9-120 Midtone Base*, 9-140 Ultra Deep Base*.

*Must be tinted before use. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

FEATURES / BENEFITS

- Feature
Premium paint & primer in one
High hiding coverage
Washable & long-lasting
Provides a mildew resistant coating
100% acrylic latex
Excellent flow & leveling
Low odor, Zero VOC**

PRODUCT DATA

Table with 2 columns: Property and Value. Includes PRODUCT TYPE: 100% Acrylic Latex, SHEEN*: Flat: 1-4 @60°; 2-4 @85°, VOLUME SOLIDS*: 35% +/- 2%, WEIGHT SOLIDS*: 50% +/- 2%, WEIGHT/GALLON*: 10.8 lbs. (4.9 kg) +/- 0.2 lbs. (91 g), VOC: 0 g/L (0.0 lbs./gal.)**

*Product data calculated on product 9-110XI

COVERAGE: Up to 400 sq. ft. (37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Table with 2 columns: Property and Value. Includes Wet Film Thickness: 4.0 mils, Wet Microns: 102, Dry Film Thickness: 1.4 mils, Dry Microns: 36

Coverage figures do not include material loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some surfaces including uncoated substrates, repaired surfaces, porous surfaces, stained areas, and drastic color changes may require a primer or more than one coat to achieve a uniform finish and complete hide.

Table with 2 columns: Property and Value. Includes DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity, To Touch: 30-60 minutes, To Recoat: 2-4 hours, To Full Cure: 30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement.

CLEANUP: Clean brushes and tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

**Colorants added to this base paint may increase VOC level significantly depending on color choice. However, PPG Futurity and PPG HS colorants (96-xxxXI, 96-xxx, 96-xxxx, 96-xxxxx), even if used at maximum tint load in any color, contributes less than 8 g/L of VOC to the final tinted product.

Read Label and Safety Data Sheet prior to use. See other cautions on last page.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Plaster, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. When applied to an uncoated substrate or to bare wood, two coats are required with the first coat acting as the primer. For severe stains, water marks, and other challenging conditions, such as bare metal or chalky surfaces, use an appropriate specialty primer.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

CONCRETE: New concrete should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10 before painting.

CONCRETE/MASONRY BLOCK: Mortar should cure for at least 30 days and preferably 90 days prior to painting. Fill block with an appropriate block filler. Surfaces previously coated with water thinned cement-based paint must be prepared with extra care. If the material appears to be adhering tightly, a masonry sealer may be applied to seal the surface. Check adhesion by applying a piece of masking tape. If the sealer peels off and has loose particles, remove all chalking or crumbling material, re-seal and re-check adhesion.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed with a metal primer.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to painting.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean. Any knots or resinous areas must be primed before painting. Countersink all nails, putty flush with surface.

PRIMERS

Concrete	4-603XI, 17-921XI, Self-priming
Concrete/Masonry Block	6-7, 6-15XI
Ferrous Metal	4020, 90-1908, 90-1909, 90-1912
Gypsum Wallboard-Drywall	6-2, 6-4, 9-900, 12-900XI, Self-priming
Plaster	4-603XI, 17-921XI, Self-priming
Wood	6-2, 9-900, 12-900XI, 17-921XI, Self-priming

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).

Not recommended for use on floors or in high humidity areas.

PROTECT FROM FREEZING.

PACKAGING

- Quart (946 mL)
- 1-Gallon (3.78 L)
- 5-Gallon (18.9 L)

Not all products are available in all sizes.

APPLICATION INFORMATION

Stir thoroughly. When using more than one can of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our website or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad or by spray equipment

Airless Spray: For airless spray application, use tip size .015" - .019" and minimum pressure of 2000 psi. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover

Thinning: DO NOT THIN

Permissible temperatures during application:

Material: 50 to 90°F 10 to 32°C

Ambient: 50 to 90°F 10 to 32°C

Substrate: 50 to 90°F 10 to 32°C

PRECAUTIONS

WARNING! HARMFUL IF INHALED. HARMFUL IF SWALLOWED. Do not breathe vapor or mist. Do not swallow. Keep container tightly closed and sealed until ready for use. Wash thoroughly after handling. Provide fresh air ventilation during and after application and drying. Avoid the inhalation of dust, particulates, spray or mist arising from the application of this preparation. Use personal protective equipment as required. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information. FIRST AID:** If swallowed, rinse mouth with water (only if the person is conscious). Call physician immediately. Do not induce vomiting unless directed to do so by medical personnel. If in eyes, rinse with water for 15 minutes. Check for and remove any contact lenses. If on skin, rinse well with water. Wash with soap and water. Get medical attention if irritation develops. If inhaled, remove to fresh air. Call physician immediately. Contains isothiazolinones. May cause allergic reaction. Keep out of the reach of children. For workplace use, an SDS is available from your retailer or by calling (412) 492-5555. EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.).

© 2024 PPG Industries, Inc. All Rights Reserved. *Pure Performance* is a registered trademark of PPG Architectural Finishes, Inc. The *PPG Logo* is a trademark and the *PPG Logo* is a registered trademark of PPG Industries Ohio, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.

