

Architectural Coatings

Speedhide Interior/Exterior Prime, Fill & High Build Latex Semi-Gloss Finish**GENERAL DESCRIPTION**

Our best professional high build latex formulated to meet the performance requirements of professional applicators. *Speedhide* Prime, Fill & High Build Latex Finish contains a water-reducible, vinyl acrylic resin with a pigment combination that provides a durable, semi-gloss finish. This product has the ability to apply heavy film build on surfaces providing improved hide over conventional coatings. Recommended for use on properly prepared interior or exterior bare porous surfaces of cement, concrete and lightweight masonry blocks where no unusual exposure conditions to moisture, heat, or humidity exist. This product primes, fills and finishes in one application.

RECOMMENDED SUBSTRATES

Brick	Masonry
Concrete	Plaster
Concrete Block (CMU)	

CONFORMANCE STANDARDS

Compliant with all US VOC regulations as of 08/2026

PRODUCT INFORMATION

6-507XI White*

*May be tinted with up to 4 oz. colorant per gallon. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PACKAGING

5-Gallon (18.9 L)

PRODUCT DATA

PRODUCT TYPE:	Vinyl Acrylic Latex
SHEEN:	Semi-Gloss, 35-45 @ 60°
VOLUME SOLIDS*:	40% +/- 2%
WEIGHT SOLIDS*:	51% +/- 2%
WEIGHT/GALLON*:	10.0 lbs. (4.5 kg) +/- 0.2 lbs. (91 g)
VOC:	< 50 g/L (0.4 lbs./gal.)

COVERAGE: Approximately 100 sq. ft. (9 sq. meters) per U.S. gallon (3.78 L).

Wet Film Thickness:	16 mils
Wet Microns:	406
Dry Film Thickness:	6.4 mils
Dry Microns:	163

Coverage figures do not include loss due to surface irregularities and porosity, or material loss due to application method or mixing. Some colors, drastic color changes, or porous surfaces may require more than one coat to achieve a uniform finish.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch:	2 hours
To Recoat:	24 hours

Drying times listed may vary depending on temperature, humidity, color, film build, and air movement.

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

LIMITATIONS OF USE

Apply only when air, surface, and product temperatures are above 50°F (10°C) and the surface temperature is at least 5°F (3°C) above the dew point. Avoid exterior painting late in the day when dew and condensation are likely to form or if rain is threatening.

One coat is needed for blocks with small pores. Two coats or more may be necessary over extremely porous Haydite or cinder block. Do not apply over surfaces treated with silicone type water repellants.

PROTECT FROM FREEZING.

FEATURES / BENEFITS**Features**

- Excellent Application Properties
- Excellent Adhesion
- Self-Priming Filler-Finish Coat
- Excellent Washability & Scrubbability
- Crack, Dirt and Pinhole Resistant
- Waterborne Formula

Benefits

- Provides for quick application
- Sticks to difficult surfaces
- Turns jobs quickly and reduces labor expenses
- Withstands repeated cleaning
- Provides for extended new look
- Soap and water cleanup

Read Label and Safety Data Sheet prior to use. See other cautions on last page.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease and any other surface contaminants. Soft, crumbly surface layers of previous coatings softened by water must be completely removed. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. All large voids, cracks, and surface imperfections should be filled with cement-sand grout. Surfaces of "hot" cement-sand grout require spot priming with a PPC alkali-resistant primer. Concrete and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. Sand all glossy, rough, and patched surfaces.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted, NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

BRICK: New brick and mortar should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10. Painting glazed brick is not recommended due to potential adhesion problems.

CONCRETE and MASONRY: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to painting. The pH of the substrate must be less than 10.

CONCRETE BLOCK (CMU): Mortar should cure for at least 30 days and preferably 90 days prior to painting.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to painting. The pH of the substrate must be less than 10.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one container of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by airless spray equipment.

Airless Spray: For airless spray application, use tip size .019" to .027" and pressure range of 2700 psi. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Nylon/Polyester Brush

Roller (nap roller cover): 3/8" - smooth; 1/2"-3/4" - semi-rough; 1"-1 1/4" - rough

Thinning: Do not thin.

Permissible temperatures during application:

Material: 50 to 90°F (10 to 32°C)

Ambient: 50 to 100°F (10 to 38°C)

Substrate: 50 to 100°F (10 to 38°C)

PRECAUTIONS

For warning information, please refer to the product label and SDS available at the online listing for this product at www.pittsburghpaintsco.com. Keep container tightly closed and sealed until ready for use. SDS, spill, and emergency information are available by calling 1-833-477-1553.

© 2026 The Pittsburgh Paints Co. All Rights Reserved. Speedhide is a registered trademark, and the P Logo & Pittsburgh Paints are trademarks of The Pittsburgh Paints Co.

The Pittsburgh Paints Co. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.



The Pittsburgh Paints Company
500 Cranberry Woods Drive
Cranberry Township, PA 16066
www.pittsburghpaints.com

Technical Services
1-800-441-9695

6-507XI - 8/2026