UC65307C

PPG Architectural Coatings

High Build Flat Interior Latex Paint

GENERAL DESCRIPTION

Recommended for use on interior walls and ceilings.

RECOMMENDED SUBSTRATES

- Interior drywall and dry joint cement.
- Previously painted drywall, plaster, masonry, wood, and metal surfaces.

CONFORMANCE STANDARDS

- Complies with the Canadian Volatile Organic Compound Concentration Limits for Architectural Coatings Regulations.

TINTING AND BASE INFORMATION

Refer to the appropriate colour formula book, automatic tinting equipment, and/or computer colour-matching system for colour formulas and tinting instructions.

UC65307 White

Some colours, drastic colour changes, or porous surfaces may require additional coats of paint to achieve a uniform finish.

PACKAGING

3.78 L
18.9 L

PRODUCT DATA

PRODUCT TYPE: Latex Paint
GLOSS: Flat: 1 to 3% (60° Gloss Meter)
VOLUME SOLIDS*: 28% ± 2%
WEIGHT SOLIDS*: 48% ± 2%
VOC*: < 50 g/L
DENSITY*: 1.4 kg/L
*Product data calculated on product UC65307C.

SPREADING RATE PER COAT Approximately 37 square metres (400 sq. ft.) per 3.78 litres on primed, smooth, nonporous surfaces.
Wet Film Thickness: 4.0 mils (102 microns)
Dry Film Thickness: 1.1 mils (28 microns)
Coverage figures do not include material loss due to application.
DRYING TIME: Dry time @ 25°C (77°F); 50% relative humidity.
To Touch: 1 hour
To Recoat: 2 to 4 hours minimum
To full Cure: 30 days
Drying times listed may vary depending on temperature, humidity, colour, film build, and air movement.
Permissible temperatures during the application:

Material:	10 to 32°C	50 to 90°F
Ambient:	10 to 32°C	50 to 90°F
Substrate:	10 to 32°C	50 to 90°F

CLEANUP: Clean tools with warm, soapy water.

WASHING INSTRUCTIONS: Wait at least 30 days before cleaning the surface and use a non-abrasive, mild cleaner.
DISPOSAL: Consult your municipality about proper disposal procedure of residue in accordance with the laws and respect the environment. Do not pour down a drain or storm sewer.

FLASH POINT: Over 93 °C (200 °F)

FEATURES / BENEFITS

Features	Benefits
Excellent Touch-Up Properties	Saves money; less material required.
Soap and water clean-up	Safe waterborne formula.

LIMITATIONS OF USE

FOR INTERIOR USE ONLY.

PROTECT FROM FREEZING.

Apply only when air, product, and surface temperatures are above 10°C (50°F).

Not recommended for use on steps, floors or other heavy traffic areas.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks or open seams. Sand all glossy, rough, and patched surfaces.

Primers: Prime all bare wood, gypsum, plaster, masonry, metal, and porous surfaces with an appropriate primer.

Concrete, Stucco, or Masonry: Plaster, concrete, and masonry must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. Remove surface dust and prime entire surface prior to painting.

Previously Painted Alkyd Surfaces in Good Condition: Prime surface with an appropriate primer.

Mildew: Remove mildew with a solution of household bleach (1 part household bleach to 3 parts of water). Before use, be sure to read and follow the instructions and warnings on the label.

PRECAUTION: Dry sanding will give rise to dust and/or hazardous fumes. Wear suitable respiratory protective equipment. WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. Contact a regional Health Canada office for more information.

GALVANIZED STEEL: A primer is required for proper adhesion. Caution must be used when selecting coatings for use on all galvanized metal surfaces. These substrates may have a factory-applied stabilizer, which is used to prevent white rusting during storage and shipping. Such stabilizers must be removed by either brush blasting, sanding or chemical treatment prior to priming.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust, prior to painting. This product is self-priming for previously painted walls, ceilings and trim in good condition. However, when applied to new drywall, two coats are required with the first coat acting as the primer.

METAL: Prior to priming and top coating, the surface must be cleaned thoroughly to remove any dust, rust, oil and surface contaminants.

PLASTER: Plaster or other alkaline surfaces should be allowed to cure for at least 30 days prior to prime with an alkali resistant primer.

WOOD: Unpainted wood or wood in poor condition should be sanded smooth, wiped clean. Any knots or resinous areas must be primed before painting. Countersink all nails or screws, putty flush with the surface prior to painting. Woods such as redwood, cedar, mahogany and Douglas fir containing tannic acid which tends to migrate to the surface should be prime prior to painting.

WATER-SOLUBLE STAINS: Apply a SEAL GRIP® primer over the stained area prior to coating, to avoid bleeding the stain into the topcoat.

Contact your local representative for any additional surface preparation guidelines.

RECOMMENDED PRIMERS

Concrete, Masonry	6-7C (Block Fillers), 4-603C, 17-921C (Primers-sealers)
Ferrous Metal	6-208C, 6-212C
Galvanized Steel	90-712C
Gypsum Wallboard-Drywall	6-2C, 6-4C, 9-900C, 12-900C, self-priming
Plaster	4-603C, 9-900C, 17-921C
Wood	6-2C, 9 900C, 12-900C, 17-921C

APPLICATION INFORMATION

Stir thoroughly. Do not thin.

Application Equipment: Apply with a high-quality brush (polyester/nylon), roller (nap size – 10 mm for smooth surfaces, 13 mm for ceilings, and up to 20 mm for rough or textured surfaces), paint pad, or by airless spray equipment. When using more than one container of the same colour, intermix to ensure colour uniformity. Where necessary, apply a second coat.

Brush: High quality polyester/nylon brush.
Roller: 10 to 20 mm (3/8 – 3/4 in.) nap synthetic roller cover.
Airless Spray: Pressure 2000 psi, tip 0.015 in. - 0.021 in.
Spray equipment must be handled with due care and in accordance with the manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Thinning: Thinning is not usually required. If necessary, add no more than 118 mL of water per 3.78L of paint.

PRECAUTIONS

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION. Avoid breathing vapours, spray or mists. Avoid contact with skin and eyes. Wear protective gloves/clothing and eye/face protection. Keep out of reach of children. **FIRST AID TREATMENT:** If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If breathed in, move person to fresh air. Contains: Limestone; titanium dioxide; Kaolin; Diatomaceous earth; crystalline silica, respirable powder (<10 microns). Sanding and grinding dusts may be harmful if inhaled. This product contains crystalline silica which can cause lung cancer or silicosis. The risk of cancer depends on the duration and level of exposure to dust from sanding surfaces or mist from spray applications. Contains isothiazolinones. May cause allergic reaction. Keep container tightly closed and sealed until ready for use. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426 (Canada). EMERGENCY SPILL INFORMATION: (412) 434-4515 (U.S.), (514) 645-1320 (Canada).

LIMITED WARRANTY

PPG Architectural Coatings Canada, Inc. warrants performance of its products to its intended use if properly applied in accordance with the label directions and the specifications of the technical data sheet. Having no control over the application methods and conditions or the circumstances related to its use, no other warranty, expressed or implied, statutory or otherwise is given. This limited warranty extends only to the original purchaser of the product and is not transferable or assignable. If the product fails to conform to this limited warranty, we will, at your option, furnish replacement product or refund the purchase price. This limited warranty excludes (1) labour or costs of labour for the application or removal of any product and (2) all other direct, indirect, incidental, special, or consequential damages.

The *PPG Logo* is a registered trademark of PPG Industries Ohio, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate: however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1 866 660-2220.

PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpaints.com

PPG Architectural Coatings Canada, Inc.
1550, rue Ampère, Suite 500
Boucherville (Québec) Canada J4B 7L4

Technical Services 1 866 660-2220
Fax: 1 800 278-8893

Architect/Specifier
1-888-PPG-IDEA