



Architectural Coatings

WALLPRO Interior PVA Primer

GENERAL DESCRIPTION

WALLPRO Interior PVA Primer is recommended for use on properly prepared interior wallboard and drywall surfaces, wood, and oriented strand board. Can be used as a primer for oil, alkyd, or latex paints.

RECOMMENDED SUBSTRATES

Gypsum Wallboard-Drywall
Oriented Strand Board
Particle Board
Wood

CONFORMANCE STANDARDS

- ✓ VOC compliant- lower than current Canadian AIM Regulations
- ✓ Can help earn LEED® 2009 credits

APPLICATION INFORMATION

Stir thoroughly. When using more than one container of the same colour, intermix to ensure colour uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Material Safety Data Sheet (MSDS) information prior to use. MSDS are available through our website or by calling 1-800-441-9695.

Application Equipment: Apply with a high quality brush, roller, paint pad, or by airless spray equipment. Where necessary, apply a second coat.

Airless Spray: Pressure 2000 psi, tip 0.015" - 0.021"
Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: High Quality Polyester/Nylon Brush

Roller: 3/8" - 3/4" nap roller cover

Thinning: Thinning is not usually required. If necessary, thin with up to 118mL of water per 3.78 L of paint.

Permissible temperatures during application:

Material: 10 to 32°C
Ambient: 10 to 32°C
Substrate: 10 to 32°C

FEATURES / BENEFITS

Features

Less than <50 g/L VOC
Good adhesion
Good sealing properties
Easy to apply
Waterborne formula
Can help earn LEED 2009 credits

TINTING AND BASE INFORMATION

Refer to the appropriate colour formula book, automatic tinting equipment, and or computer colour matching system for colour formulas and tinting instructions.

34-2C

White (Tintable)

Some colour, drastic colour changes, or porous surfaces may require more than one coat to achieve a uniform finish.

PRODUCT DATA

PRODUCT TYPE: Vinyl Acrylic Latex
SHEEN: Flat
VOLUME SOLIDS: 25% +/- 2%
WEIGHT SOLIDS: 39% +/- 2%
VOC: <50 g/L

WEIGHT/GALLON: 4.8 kg +/- 91 g

COVERAGE: Approximately 37 sq. m/3.78 L per 3.78 L on smooth, nonporous surfaces.

Wet Film Thickness: 4.0 mils
Wet Microns: 102
Dry Film Thickness: 1.0 mils
Dry Microns: 25.4

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @ 25°C; 50% relative humidity.

To Touch: 30 minutes

To Recoat: 4 hours

Drying times listed may vary depending on temperature, humidity, film build, colour, and air movement.

CLEANUP: Clean tools with warm soapy water

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 93°C

GENERAL SURFACE PREPARATION

Surfaces to be coated must be dry, clean, sound, and free from all contamination including loose and peeling paint, dirt, grease, oil, wax, concrete curing agents and bond breakers, chalk, efflorescence, mildew, rust, product fines, and dust. Remove loose paint, chalk, and efflorescence by wire brushing, scraping, sanding, and/or pressure washing. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Feather back all rough edges to sound surface by sanding.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. **LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE.** Wear a properly fitted NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. In Canada contact a regional Health Canada office. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust before priming the substrate.

ORIENTED STRAND BOARD: Countersink all nails or screws and putty flush with the surface. Surface should be cleaned to remove any dust or contaminants before priming the substrate.

PARTICLE BOARD: Countersink all nails or screws and putty flush with the surface. Surface should be cleaned to remove any dust or contaminants before priming the substrate. (Veneered surfaces should be sanded smooth and cleaned to remove any dust or contaminants, before priming the substrate.)

WOOD: Unpainted wood or wood in poor condition should be sanded smooth and wiped clean before priming the substrate. Spot prime knots or resinous areas before the application of the first full coat of primer. Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust before priming the substrate.

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, surface and product temperatures are between 10°C and 32°C.

Not recommended for use on floors.

PROTECT FROM FREEZING.

PACKAGING

3.78 L

18.9 L

The PPG logo is a registered trademark and Ecological Solutions from PPG is a trademark of PPG Industries, Ohio, Inc. **WALLPRO** is a trademark of PPG Architectural Finishes, Inc. **LEED** is a registered trademark of the US Green Building Council.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-800-441-9695.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpro.com

Technical Services
1-800-441-9695
1-888-807-5123 fax

Architect/Specifier
1-888-PPG-IDEA

PPG Canada, Inc.
Architectural Coatings
4 Kenview Blvd
Brampton, ON L6T 5E4

A1.48C 3/2012