

Architectural Coatings

Speedhide Exterior 100% Acrylic Latex Flat

GENERAL DESCRIPTION

Speedhide Exterior 100% Acrylic Latex Flat is a durable, 100% acrylic exterior paint designed for new and repaint applications where durability and ease of application are most important in both the commercial and multi-family markets. This less than 50 g/L VOC paint provides excellent flow and leveling, very good hide and coverage and has excellent resistance to mildew on the paint film. This 100% acrylic workhorse formula also provides excellent adhesion and can be applied at temperatures as low as 35°F (2°C) extending your painting season. Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

RECOMMENDED SUBSTRATES

Aluminum	Ferrous Metal	Stucco
Brick	Fiber Cement	Vinyl
Concrete	Masonry	Wood

CONFORMANCE STANDARDS

Compliant with all US VOC Regulations as of 10/2026
MPI Approved in Category #10

PRODUCT INFORMATION

6-610XI	White
6-650XI	White & Pastel Base
6-651XI	Midtone Base*
6-653XI	Ultra Deep Base*

*Must be tinted before use. Refer to the appropriate color formula book, automatic tinting equipment, and or computer color matching system for color formulas and tinting instructions.

PACKAGING

1-Gallon (3.78 L)
5-Gallon (18.9 L)

Not all products are available in all sizes.

FEATURES / BENEFITS

Features

Excellent Adhesion
100% Acrylic Latex Formulation
Low VOC, < 50g/L
Provides Uniform Film and Appearance
Excellent Application Properties
Provides Mildew Resistant Coating
Good UV and Weathering Resistance
Application Down to 35°F (2°C)
MPI #10 Approval

PRODUCT DATA

PRODUCT TYPE:	100% Acrylic Latex
SHEEN:	Flat: 0-5 @60°; 0-5 @85°
VOLUME SOLIDS*:	34% +/- 2%
WEIGHT SOLIDS*:	48% +/- 2%
WEIGHT/GALLON*:	10.5 lbs. (4.8 kg) +/- 0.2 lbs. (91 g)
VOC:	< 50 g/L (0.4 lbs./gal.)

*Product data calculated on product 6-650XI.

COVERAGE: Approximately 400 sq. ft. (37 sq. meters) per U.S. Gallon (3.78L) on smooth, nonporous surfaces.

Wet Film Thickness:	4.0 mils
Wet Microns:	102
Dry Film Thickness:	1.4 mils
Dry Microns:	36

Coverage figures do not include loss due to surface irregularities and porosity or material loss due to application method or mixing.

DRYING TIME: Dry time @ 77°F (25°C); 50% relative humidity.

To Touch:	1 hour
To Recoat:	2-4 hours
To Full Cure:	30 days

Drying times listed may vary depending on temperature, humidity, film build, color, and air movement. For example, product applied at 35°F (2°C) would require a minimum of 24 hours before recoat.

CLEANUP: Clean tools with warm, soapy water. DANGER – RAGS, STEEL WOOL, OR WASTE SOAKED WITH *SPEEDHIDE* PAINT MAY SPONTANEOUSLY CATCH FIRE IF IMPROPERLY DISCARDED. IMMEDIATELY AFTER EACH USE, PLACE RAGS, STEEL WOOL, OR WASTE IN A SEALED, WATER-FILLED, METAL CONTAINER.

DISPOSAL: Contact your local environmental regulatory agency for guidance on disposal of unused product. Do not pour down a drain or storm sewer.

FLASH POINT: Over 200°F (93°C)

Benefits

Minimizes cracking and peeling
Excellent longevity and overall durability
Meets the most stringent VOC regulations nationwide
Hides surface imperfections
Built for easy and effective application
Resists the formation of mold and mildew on the paint film
Holds up to harsh outdoor elements
Extends the painting season
Meets strict performance and aesthetic requirements

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, mildew, grease, oil, chalk, rust, and any other surface contaminants. Blistering and peeling issues are commonly caused by moisture behind the paint film. Problems leading to excessive moisture in the substrate must be repaired prior to painting. Putty all nail holes and caulk all cracks and open seams. Sand all glossy, rough, and patched surfaces. Stucco, concrete, and masonry surfaces must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. An appropriate primer is recommended for all uncoated surfaces and special substrates, such as tannin staining wood, new or chalky masonry, and bare metal.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust or fumes. LEAD IS TOXIC. EXPOSURE TO LEAD DUST OR FUMES CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a properly fitted, NIOSH-approved respirator and prevent skin contact to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by contacting the USEPA National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead. Follow these instructions to control exposure to other hazardous substances that may be released during surface preparation.

ALUMINUM: This substrate may present potential adhesion problems. Any coating applied directly to aluminum should be spot applied, allowed to cure overnight, and then evaluated for adhesion. If adhesion is good, the application may proceed.

BRICK: New brick and mortar should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Painting glazed brick is not recommended due to potential adhesion problems.

CONCRETE and MASONRY: New concrete should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming with an alkali resistant primer.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

FIBER CEMENT: Fiber cement siding and trim board may present potential adhesion, alkali burn, and efflorescence problems. New board should be aged for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 and the moisture content must be less than 12% prior to priming and topcoating. All cracks and opens seams should be caulked to prevent water penetration. Pre-primed board from the manufacturer may not be uniformly or completely sealed. It is recommended that an alkali resistant primer be applied to ensure complete and uniform sealing prior to topcoating.

STUCCO: New stucco should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Surface chalk from the curing or aging process should be removed then sealed with an appropriate sealer to rebind and restore the surface to a sound condition.

VINYL and ARCHITECTURAL PLASTIC: Vinyl and similar architectural plastics may present potential adhesion problems. A primer may be required to promote proper adhesion. Consult the manufacturer's guidelines prior to painting. Primer and topcoat should be spot applied, allowed to cure overnight, then evaluated for adhesion. If adhesion is good, the application may proceed. Check adhesion by applying a piece of masking tape. When the masking tape is removed, if the coating peels off, the surface must be scuff sanded prior to proceeding to ensure mechanical adhesion. Vinyl siding and similar plastic composites should not be painted with a color darker than the original color. Painting vinyl siding or plastic composites with a darker color may cause them to warp. Color selection for use over vinyl siding is limited. For information, call 1-800-441-9695.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be primed before painting.

RECOMMENDED PRIMERS

Aluminum	17-921XI
Brick	4-503, 4-603XI, 17-921XI
Concrete & Masonry	4-503, 4-603XI, 17-921XI
Ferrous Metal	90-1908, 90-1909, 90-1912
Fiber Cement	4-2, 4-503, 4-603XI
Stucco	4-2, 4-503, 4-603XI, 4-808, 4-809, 4-898
Vinyl	17-921XI
Wood	17-921XI

LIMITATIONS OF USE

Apply only when air, surface, and product temperatures are between 35°F (2°C) and 90°F (32°C) and at least 5°F (3°C) above the dew point. Air and surface temperatures must remain between 35°F (2°C) and 90°F (32°C) for the next 48 hours. Avoid painting in direct sunlight or on hot surfaces. Do not apply late in the day when dew and condensation are likely to form or if rain or snow is expected. On large expanses of metal, temperatures must be 50°F (10°C) or higher.

PROTECT FROM FREEZING.

Not recommended for use on steps or floors.

While this product provides a mildew resistant coating, growth may still occur if the substrate is not properly prepared prior to painting and/or if the substrate is consistently exposed to conditions conducive to mold, mildew, and algae.

APPLICATION INFORMATION

Stir thoroughly before using and occasionally when in use. When using more than one container of the same color, intermix to ensure color uniformity. USE WITH ADEQUATE VENTILATION. KEEP OUT OF REACH OF CHILDREN. Read all label and Safety Data Sheet (SDS) information prior to use. SDS are available through our web site or by calling 1-800-441-9695.

Application Equipment: Apply with a high-quality brush, roller (nap size – 3/8" for smooth surfaces and up to 3/4" for rough or textured surfaces), paint pad, or by spray equipment.

Airless Spray: For airless spray application, use tip size .015" to .021" and pressure range of 1500 to 2000 psi. Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

Brush: Polyester/Nylon Brush

Roller (nap roller cover): 3/8" - 3/4"

Thinning: Do not thin.

Permissible temperatures during application:

Material: 35 to 90°F (2 to 32°C)

Ambient: 35 to 90°F (2 to 32°C)

Substrate: 35 to 90°F (2 to 32°C)

PRECAUTIONS

For warning information, please refer to the product label and SDS available at the online listing for this product at www.pittsburghpaintsco.com. Keep container tightly closed and sealed until ready for use. SDS, spill, and emergency information are available by calling 1-833-477-1553.

© 2026 The Pittsburgh Paints Co. All Rights Reserved. *Speedhide* is a registered trademark, and the *P Logo* & *Pittsburgh Paints* are trademarks of The Pittsburgh Paints Co.

The Pittsburgh Paints Co. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, call 1-800-441-9695.



**PITTSBURGH
PAINTS CO.**

The Pittsburgh Paints Company
500 Cranberry Woods Drive
Cranberry Township, PA 16066
www.pittsburghpaints.com

Technical Services
1-800-441-9695

6-610XI - 10/2026