

GENERAL DESCRIPTION

PPG Interior Latex Flat Ceiling Paint is a good quality interior flat latex ceiling paint designed for high production work where a brighter white ceiling paint is required. Ideal for use on properly prepared, interior ceilings composed of primed or previously painted drywall, plaster, masonry, and wood.

RECOMMENDED SUBSTRATES

Masonry/Concrete Stucco
Painted drywall
Plaster
Wood

CONFORMANCE STANDARDS

- Complies with the Canadian Volatile Organic Compound Concentration Limits for Architectural Coatings Regulations.

TINTING AND BASE INFORMATION

Refer to the appropriate colour formula book, automatic tinting equipment, and/or computer colour-matching system for colour formulas and tinting instructions.

9585C White

Some colours, drastic colour changes, or porous substrates may require more than one coat to achieve a uniform finish.

PACKAGING

3.78 L

PRODUCT DATA

PRODUCT TYPE: Vinyl Acrylic Latex
SHEEN: Flat: 0 to 3 % (60° and 85° Gloss Meter)
VOLUME SOLIDS*: 29% ± 2%
WEIGHT SOLIDS*: 48% ± 2%
VOC*: <50 g/L (0.4 lbs./gal.)

SPREADING RATE PER COAT: Approximately 37 m² (400 ft²) per 3.78 litres on smooth and nonporous surfaces.

Wet Film Thickness: 4 mils
Wet Microns: 102
Dry Film Thickness: 1.2 mils
Dry Microns: 30

Coverage figures do not include material loss due to application. Some colours, drastic colour changes, or porous surfaces may require additional coats of paint to achieve a uniform finish.

DRYING: Dry time @ 25°C (77°F); 50% relative humidity.

To Touch: 30 minutes
To Recoat: 4 hours
Full curing: 30 days

Drying times listed may vary depending on temperature, humidity, colour, film build, and air movement.

Permissible temperatures during the application:

Material:	10 to 32°C	50 to 90°F
Ambient:	10 to 32°C	50 to 90°F
Substrate:	10 to 32°C	50 to 90°F

CLEANUP: Clean tools with warm, soapy water.

DISPOSAL: Consult your municipality about proper disposal procedure of residue in accordance with the laws and respect the environment. Do not pour down a drain or storm sewer.

FLASH POINT: Over 93.3°C (200°F)

FEATURES / BENEFITS

Features

Excellent Uniformity.
Good Hiding.
Non-Yellowing.
Good Touch-Up.
Easy Soap and Water Clean-Up.

Benefits

Prevents flat and glossy spots.
Smooth finish hiding imperfections.
Colors stay true longer.
Extends time to repaint.
No solvent disposal issues.

PERFORMANCE DATA

LIMITATIONS OF USE

FOR INTERIOR USE ONLY. Apply when air, product and surface temperatures are between 50°F (10°C) and 90°F (32°C).
PROTECT FROM FREEZING.

GENERAL SURFACE PREPARATION

Surface must be clean and dry. Remove all loose, peeling paint, dirt, grease, and any other surface contaminants. Putty all nail holes and caulk all cracks or open seams. Sand all glossy, rough, and patched surfaces.

PRECAUTION: Dry sanding will give rise to dust and/or hazardous fumes. Wear suitable respiratory protective equipment. **WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. **LEAD IS TOXIC.** Contact a regional Health Canada office for more information.

Primers: Prime all bare surfaces with the appropriate primer.

Concrete, Stucco, or Masonry: Plaster, concrete, and masonry must be completely dry, free of efflorescence, and allowed to cure for 30 days prior to painting. Remove surface dust and prime entire surface prior to painting.

Previously Painted Alkyd Surfaces in Good Condition: Prime surface with an appropriate primer.

CONCRETE and MASONRY: New concrete and masonry should cure for at least 30 days and preferably 90 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

FERROUS METAL: The surface must be cleaned thoroughly to remove any dust, rust, and surface contaminants, and then primed.

GYPSUM WALLBOARD-DRYWALL: Nails or screws should be countersunk, and they along with any indentations should be mudded flush with the surface, sanded smooth and cleaned to remove any dust prior to painting the substrate.

PLASTER: Plaster, hardcoat, skim coat, or other alkaline surfaces should be allowed to cure for at least 30 days prior to priming and painting. The pH of the substrate must be less than 10 before priming. Use of an alkali resistant primer is recommended.

WOOD: Countersink all nails, putty flush with surface. Unpainted wood or wood in poor condition should be sanded smooth, wiped clean, then primed. Any knots or resinous areas must be sealed before painting.

Before use, be sure to read and follow the instructions and warnings on the label and Safety Data Sheet. See other cautions on the last page.

RECOMMENDED PRIMERS

Concrete/Masonry:	17-921XIC, 4-809C
Ferrous Metal:	4020, 90-712C
Gypsum Wallboard-Drywall:	6-2, 6-4, 9-900, 34-2C, 12-900XIC
Plaster:	17-921XIC
Wood:	6-2, 9-900, 17-921XIC, 34-2C

APPLICATION INFORMATION

Stir thoroughly. Do not thin. Apply with a high-quality brush (polyester/nylon), roller (nap size – 13 mm), paint pad, or by airless spray equipment. When using more than one container of the same colour, intermix to ensure colour uniformity. Apply only when air, surface, and product temperatures are between 10°C (50°F) and 32°C (90°F).

Where necessary, apply a second coat and allow each coat to dry thoroughly before applying the next coat.

Airless Spray: Pressure 1500 to 2000 psi; tip 0.015" to 0.021". Spray equipment must be handled with due care and in accordance with manufacturer's recommendation. High-pressure injection of coatings into the skin by airless equipment may cause serious injury.

PRECAUTIONS

MAY BE HARMFUL IF SWALLOWED. MAY CAUSE EYE AND SKIN IRRITATION. Avoid breathing vapours, spray, or mists. Avoid contact with skin and eyes. Wear protective gloves/clothing and eye/face protection. Keep out of reach of children. Keep container tightly closed and sealed until ready for use. **Note: These warnings encompass the product series. Prior to use, read and follow product-specific SDS and label information.** **FIRST AID TREATMENT:** If swallowed, call a Poison Control Centre or doctor immediately. If in eyes or on skin, rinse well with water. If breathed in, move person to fresh air. Contains: limestone; titanium dioxide; kaolin; diatomaceous earth; calcium carbonate. For workplace use, an SDS is available from your retailer or by calling 1-800-463-7426. EMERGENCY SPILL INFORMATION: 514-645-1320.

LIMITED WARRANTY

PPG Architectural Coatings Canada, Inc. warrants performance of its products to its intended use if properly applied in accordance with the label directions and the specifications of the technical data sheet. Having no control over the application methods and conditions or the circumstances related to its use, no other warranty, expressed or implied, statutory or otherwise is given. This limited warranty extends only to the original purchaser of the product and is not transferable or assignable. If the product fails to conform to this limited warranty, we will, at your option, furnish replacement product or refund the purchase price. This limited warranty excludes (1) labour or costs of labour for the application or removal of any product and (2) all other direct, indirect, incidental, special, or consequential damages.

The PPG Logo is a registered trademark of PPG Industries Ohio, Inc.

PPG Architectural Finishes, Inc. believes the technical data presented is currently accurate; however, no guarantee of accuracy, comprehensiveness, or performance is given or implied. Improvements in coatings technology may cause future technical data to vary from what is in this bulletin. For complete, up-to-date technical information, visit our web site or call 1-866-660-2220.



PPG Industries, Inc.
Architectural Coatings
One PPG Place
Pittsburgh, PA 15272
www.ppgpaints.com

PPG Architectural Coatings Canada, Inc.
1550 rue Ampère, Suite 500
Boucherville (Quebec), J4B 7L4

Technical Services 1 866 660-2220

Fax: 1 800 278-8893

Architect/Specifier
1-888-PPG-IDEA